io·li·tec

### Trihexyltetradecylphosphonium dicyanamide

 Revision Date:
 12/22/2011

 Date Issued:
 2/8/2022

#### 1 IDENTIFICATION OF THE SUBSTANCE/PREPARATION AND THE COMPANY/UNDERTAKING

| Product name        | Trihexyltetradecylphosphonium   |
|---------------------|---|
|                     | dicyanamide   |
| Product code        | IN-0010   |
| CAS                 | 701921-71-3   |
| Supplier            | loLiTec<br>Ionic Liquids Technologies GmbH<br>Im Zukunftspark 9<br>D – 74076 Heilbronn<br>Germany |
| Telephone           | +49 (0)7131-89839-0   |
| Fax                 | +49 (0)7131-89839-109   |
| Emergency telephone | +49 (0)179-5322578  |
| Email               | info@iolitec.de   |

## 2 COMPOSITION/INFORMATION ON INGREDIENTS

Ingredient name

CAS No.

Empirical Formula

Trihexyltetradecylphosphonium dicyanamide 701921-71-3

C<sub>34</sub>H<sub>68</sub>N<sub>3</sub>P

⊖<sub>N(CN)2</sub>

Structure Molecular weight Purity

549.90 g/mol >95%

io·li·tec

## Trihexyltetradecylphosphonium dicyanamide

 Revision Date:
 12/22/2011

 Date Issued:
 2/8/2022

#### **3 PROPERTIES**

| Yellow to orange      |
|-----------------------|
| Liquid                |
| not available         |
| -67 °C                |
| not available         |
| 0.9 g/cm <sup>3</sup> |
| 361 mPa * s           |
| not available         |
| 0.156 mS/cm           |
| 3.2 V                 |
| 1.5 V                 |
| -1.7 V                |
|                       |

## **4 CO-SOLVENT MISCIBILITY**

| Water        | not miscible |
|--------------|--------------|
| Acetone      | miscible     |
| Acetonitrile | miscible     |
| Isopropanol  | miscible     |
| Toluene      | miscible     |
| Hexane       | not miscible |
|              |              |

io·li·tec

Trihexyltetradecylphosphonium dicyanamide

 Revision Date:
 12/22/2011

 Date Issued:
 2/8/2022

#### **5 ORDER INFORMATION**

IN-0010-HP can be obtained in the following standard quantities:

| Quantity | Price          |
|----------|----------------|
| 25 g     | Please enquire |
| 50 g     | Please enquire |
| 100 g    | Please enquire |
| 250 g    | Please enquire |
| 500 g    | Please enquire |
| 1 kg     | Please enquire |
| Bulk     | Please enquire |

Please send your order via email to <u>order@iolitec.de</u> or fax +49 (0)7131 – 89839109.

## 6 OTHER INFORMATION

#### DISCLAIMER

THE ABOVE INFORMATION IS BELIEVED TO BE CORRECT BUT DOES NOT PURPOSED TO BE ALL INCLUSIVE AND SHALL BE USED ONLY AS A GUIDE. IOLITEC SHALL NOT BE HELD LIABLE FOR ANY DAMAGE RESULTING FROM HANDLING OR FROM CONTACT WITH THE ABOVE PRODUCT. THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR ANY PROCESS. IT IS THE USERE'S RESPONISIBILTY TO SATISFY HIMSELF AS TO THE SUITABILITY OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE.

IN NO WAY SHALL IOLITEC BE LIABLE FOR ANY CLAIMS, LOSSES OR DAMAGES OF ANY THIRD PARTY OR FOR THE LOST PROFITS OR ANY SPECIAL, INDIRECT, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY



Trihexyltetradecylphosphonium dicyanamide

 Revision Date:
 12/22/2011

 Date Issued:
 2/8/2022

DAMAGES, HOWSOEVER ARISING, EVEN IF THE COMPANY HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES.